



Art no.:
G2482 | G2483
G2485 | G2486

TECHNICAL SHEET

FIBER GEL ROSE BLUSH | FIBER GEL NATURAL BLUSH

CHARACTERISTICS

- Special formula with fiberglass
- Strength of acrylics
- Benefits of gel
- Top gel can be used, but is not necessary as the gel can be polished to shine

STEP BY STEP

1. Prepare the nail according to the standard scheme.
2. Apply Purifier D2000 on the nails to remove the remaining dust.
3. Apply All System Bonding D4005, let it dry in the air 30 sec.
4. a. For regular quality nails, apply a thin base layer of Fiber Gel Rose Blush G2482-G2483 / Fiber Gel Natural Blush G2485-G2486, cure it 2 minutes under UV lamp or 1 minute under LED lamp.
b. For nails that tend to cause lifting, apply a thin layer of Base gel G0104, cure it 2 minutes under UV lamp or 1 minute under LED lamp.
5. Build the nail using Fiber Gel Rose Blush G2482-G2483 / Fiber Gel Natural Blush G2485-G2486, cure it 2 minutes under UV lamp or 1 minute under LED lamp. In order to avoid excessive heat reaction, apply gel in layers not thicker than 2 mm.
6. Remove the residual sticky layer with Gel Cleanser G8000, and file the nail in shape.
7. Apply color gel or gel polish of your choice, cure under the lamp.
8. Apply top gel of your choice to create the desired effect.



CURING TIME



120 SECONDS
36 W UV LAMP



60 SECONDS
24-48 W LED LAMP



THIXOTROPY

MEDIUM - HIGH



EXOTHERMIC REACTION

LOW



ADHESION

HIGH



PINCHABILITY

YES

TACKY RESIDUE AFTER CURING



LOW

MEDIUM

HIGH

HARDNESS



LOW

MEDIUM

HIGH

TRANSPARENCY



LOW

MEDIUM

HIGH

VISCOSITY



LOW

MEDIUM

HIGH

FLEXIBILITY



LOW

MEDIUM

HIGH

INGREDIENT LISTING

Fiber Gel Rose Blush: DI-HEMA Trimethylhexyl Dicarbamate, Urethane Acrylate Oligomer, Hydroxypropyl Methacrylate, Silica Dimethicone Silylate, Tripropylene Glycol Diacrylate, Methylbenzoyl Formate, Glass, Silica Dimethyl Silylate, CI 77891, CI 45410, CI 77491, CI 77499, p-hydroxyanisole

Fiber Gel Natural Blush: DI-HEMA Trimethylhexyl Dicarbamate, Urethane Acrylate Oligomer, Hydroxypropyl Methacrylate, Silica Dimethicone Silylate, Tripropylene Glycol Diacrylate, Methylbenzoyl Formate, Glass, Silica Dimethyl Silylate, CI 77891, CI 45410, CI 77491, CI 77499, p-hydroxyanisole

Nail Creation Headquarters

Burgemeesterlaan 2 • 6002 EG Weert • The Netherlands • Phone: +31 88 - 515 5840 • Email: info@nailcreation.com • www.nailcreation.com

V2111



NAIL CREATION.

BEST ESSENTIALS,
GREAT VALUE!

Nail Creation, since 1993

Nail Creation is an international brand for professional nail styling products that was established in 1993. Dedicated to supplying nail technicians with the best nail products available, Nail Creation has been advancing the technology of nail products in order to achieve maximum performance and perfect results. Nail Creation is among the leading brands in nail design worldwide and currently available in over 30 countries. Our largest market is Europe, where we are the market leader in several countries. Nail Creation specializes in both gel and acrylic for nail design and sculpturing.

Nail Creation is a strong brand, has a uniform international image, high-class presentation, and great profit margins. The nail industry is exceptionally dynamic and has its own unique developments and styling trends. With our own R&D department and production facilities, we have all products, know-how and training facilities in-house, which makes it possible to offer all new creative developments to the nail industry. We are committed to creating time-saving, effective products to enable technicians to work more efficiently, profitably and perfectly, nail after nail.

- **+27 years experience**
- **High quality product range**
- **Gel, acrylic and supplementary products**
- **Competitive pricing**
- **Great profit margins**
- **High-class international brand image**
- **In-house R&D department**
- **In-house production facilities**
- **Turnkey marketing concept**
- **New Partner Program**



The future in nails